




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08G 18/22, 18/08, C09D 175/04	A1	(11) International Publication Number: WO 96/20967 (43) International Publication Date: 11 July 1996 (11.07.96)
(21) International Application Number: PCT/US95/16516 (22) International Filing Date: 20 December 1995 (20.12.95) (30) Priority Data: 08/366,308 29 December 1994 (29.12.94) US (71) Applicant: MINNESOTA MINING AND MANUFACTURING COMPANY [US/US]; 3M Center, P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (72) Inventor: ENGEL, Paul, T.; P.O. Box 33427, Saint Paul, MN 55133-3427 (US). (74) Agents: O'CONNELL, Patrick, J. et al.; Minnesota Mining and Manufacturing Company, Office of Intellectual Property Counsel, P.O. Box 33427, Saint Paul, MN 55133-3427 (US).		(81) Designated States: BR, CA, CN, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>

(54) Title: REACTION SYSTEM FOR PRODUCING A POLYURETHANE AND METHOD OF USING SAME TO SEAL A SURFACE

(57) Abstract

This invention concerns a reaction system for producing a polyurethane having an isocyanate index value of at least 100, and a catalyzed reaction mixture thereof, having a gel time between 5 and 60 minutes. The reaction system, in one aspect, involves a mixture of first and second parts that are located in separate containers, respectively, which are effective to prevent contact between said first and second parts thereof until coating or sealing application is desired. This two-part reaction system includes: (a) a first part comprising a polyisocyanate component; b) a second part comprising: (i) a polyol component; (ii) a polyurethane catalyst comprising a bismuth/zinc polyurethane catalyst; and (iii) a molar excess of a complexing agent for the polyurethane catalyst, where the complexing agent is a mercaptan compound. This invention also concerns a method of forming a polyurethane sealant on a surface using the two-part reaction system and catalyzed reaction mixture.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

REACTION SYSTEM FOR PRODUCING A POLYURETHANE AND METHOD OF USING SAME TO SEAL A SURFACE

BACKGROUND OF THE INVENTION

5

This invention relates to a novel reaction system for producing a polyurethane including a unique catalyst system effective therefor. Such a reaction system finds use for example to form a sealant coating or strip.

10

It is known to formulate polyurea-urethane compositions (e.g., sealants, coatings, foams, and the like) as two pack systems. One pack includes the isocyanate-reactive components such as polyols, together, typically with a catalyst and other customary additives, while the second pack includes the polyisocyanate. The catalyst is separately packaged from the polyisocyanate in order to prevent premature gelation of the latter component. The two packs are normally mixed immediately prior to application of the coating. Upon mixing the two packs, the hydroxyl groups of the polyol chemically react with the isocyanate groups of the polyisocyanate, ultimately leading to gelation. At gelation, the reaction mixture rapidly loses its fluidity with an attendant pronounced increase in viscosity. The time associated with reaching the gelation point also is often referred to as the "potlife".

15

20

While bismuth carboxylate catalysts are known, their catalytic effect in promoting the cure of isocyanate-containing compositions is such that the rate of cure is generally linear. While such rates of cure are desirable for some applications, a curing rate is also desirable for many applications characterized by providing a slow incipient build-up of viscosity but with the reaction mixture nonetheless completely curing or curing to a tack-free state within a relatively short period of time.

25

An example of such an application is for the cure of a two-pack or part urethane adhesive composition, wherein a "pot-life" is desired during which the composition may be handled and/or applied to a substrate before it substantially cures. In this regard, certain mercury compounds are known to be useful as latent catalysts, but their use is not desirable for environmental reasons.

30

One solution is taught by US Patent 4,788,083 which describes an activatable/ complexed catalyst system which provides an extended potlife yet is readily activatable with vaporous amine or heat. The catalyst is a complexed catalyst

generally comprising the reaction product of a tin and/or bismuth polyurethane catalyst with a molar excess of a complexing agent selected from a mercapto or polyphenol compound. However, the use of vaporous amine and/or heat activation methods to incite rapid cure may present problems on a commercial scale. For example, accurate
5 dosage of the amine activator can be troublesome, which can adversely impact the appearance and resistance to yellowing. Use of heat activation requires an oven, which is impractical for operations involving large objects, such as installing and sealing a glass windshield into a car.

Laid-Open Japanese patent application JP H1-213,382 (Sakada et al.),
10 October 15, 1987, describes two component polyurethane adhesives wherein organic tin compounds are used in conjunction with multi-functional mercaptan compounds to delay the onset of cure and to provide "adaptability" (a period of workability) without undue lengthening of the adhesive hardening time.

European Patent Application Publication No. 0 454 219 (October 30,
15 1991), describes a polyurethane system which is stated to eliminate the need for the amine or heat activation required in US Patent No. 4,788,083, by use of a polyol component having an acid value of about 5 or less. The publication describes polyurethane systems having extended potlives of multiple hours.

Also, commonly assigned U.S. Patent No. 5,250,651 discloses a sealant
20 composition useful for insulation displacement connector enclosures. The sealant composition in U.S. 5,250,651 is synthesized by a reaction between polyether species and isocyanate species, requiring a stoichiometric deficit of the isocyanate reactant, that results in a gel-like polymer which is lightly cross-linked through urethane linkages.

25 Metal ion catalysis and inhibition of isocyanate reaction in the presence of mercaptans has been studied by J. Robins in *Metal Ion Catalysis In Mercaptan Isocyanate Reactions*, Advances in Urethane Science and Technology, Volume 12, Technomic Publishing Company, Lancaster, PA 17604, (1993), pp. 25-58. J. Robins classifies metal ions in three categories on the basis of their ability to complex with
30 mercapto cure inhibitors and yet act as catalysts after controlled induction period where no catalytic action is observed. Robins' three classes are: (1) metal ions which are good catalysts (e.g., In^{+3} , Tl^{+4} , Sn^{+2}); (2) metal ions which exhibit fair catalytic

activity (e.g., Zn^{+2} , Pb^{+2} , Bi^{+3} , Et_2Bi^+); (3) metal ions which show a very low catalytic activity (e.g., Ca^{+2} , Co^{+2} , Cu^{+2}); and (4) no catalytic activity (e.g., Li^+ , Na^+ , Al^{+3}).

In a paper presented at UTECH '92 co-authored by John D. Arenivar (Shepard Chemical Co.) and Kurt C. Frisch et al. (Polymer Technologies, Inc.,
5 University of Detroit Mercy), entitled "Metal Carboxylates For Urethanes", a study is discussed of the kinetics of bismuth and/or zinc carboxylate-catalyzed urethane reactions by using model compounds for the reactants in separate non-competitive reactions. The data of this study is then described as having been used to successfully formulate flexible foams, catalyzed by bismuth and zinc carboxylate compounds in the
10 absence of tertiary amine catalysts.

There also are many applications where a polyurethane sealant would be desirable which possesses a cure profile providing a sufficient induction period to tool and manipulate the contour the admixed sealant, if necessary, before the onset of cure. There also exists a need for a sealant that has a induction period that does not
15 require special activation procedures, yet, in a relatively short period of time the coated workpiece can be quickly further handled or returned to service. An example of such an application is the installing of a glass windshield into a car frame.

That is, in many applications, such as installing a glass windshield into a car frame, rapid cures are desired without the need for special activators for the
20 system. For instance, in a glass repair shop or vehicle assembly line setting for installing glass windshields, a glass sealant is desired which controllably cures or gels at a time that falls inside a time span or window beginning several minutes after admixture of the polyurethane-forming components to within about an hour after admixture. Such a cure profile would provide reasonably ample time to apply and
25 perform any necessary tooling and shaping of the sealing coating on the surface to be sealed before the reaction mixture sets-up to an extent precluding such manipulation, while avoiding unduly long open times to allow the vehicle to be returned to service or further handled as soon as possible. The period of time spanning from the mixture of the polyurethane-forming components to the gel time is often referred to as the open
30 time or induction time.

SUMMARY OF THE INVENTION

The present invention relates to a reaction system for producing a polyurethane, the catalyzed reaction mixture thereof involving a unique catalyst system therefor, and the cured polyurethane product derived therefrom. The novel reaction system for producing polyurethane meets specific temporal-related criteria of controlled onset of cure, but with rapid curing achieved shortly thereafter without the need for special activation procedures.

In one embodiment, there is a two-part reaction system for producing a polyurethane having an isocyanate index of at least 100 or greater in value from a catalyzed reaction mixture, and the polyurethane having a gel time between 5 and 60 minutes after admixture of said two parts, where the first and second parts, as two packs, are located in separate containers, respectively, which are effective to prevent contact between said first and second parts thereof until coating application is desired. This two-part reaction system includes:

- (a) a first part comprising a polyisocyanate component;
- (b) a second part comprising:
 - (i) a polyol component;
 - (ii) a polyurethane catalyst comprising a bismuth/zinc polyurethane catalyst; and
 - (iii) a molar excess of a complexing agent for the polyurethane catalyst, where the complexing agent is a mercaptan compound.

In a further embodiment, the mercaptan compound is selected from the group consisting of a mercaptoalkyl-alkoxy silane, a thioglycol, and an alkylthiol, and mixtures thereof.

The bismuth/zinc polyurethane catalyst comprises a physical mixture of a bismuth salt and a zinc salt. Preferably, the bismuth salt and zinc salt are organometallic catalytic compounds of bismuth and zinc, respectively.

The reaction system of this invention preferably employs the polyisocyanate component and the polyol component in amounts providing an isocyanate index of from 105 to 150.

In the preferred reaction systems of the present invention, in the period of time of 5 to 60 minutes after admixture of the reactants, the catalyzed systems show

at least a fivefold increase in viscosity, in centapoise, within a time span (window) of less than 10 minutes, where the viscosity is measured using a Brookfield rheometer with a T-F spindle at 2 rpm in conjunction with a helipath at a temperature of 25°C and at approximately 50% relative humidity. These systems offer a highly useful controlled
5 onset of cure together with a relatively rapid cure well-suited for applications such as windshield sealing. These systems also have wetting and tack properties compatible to the coating of a wide variety of different types of materials.

In yet another embodiment of the present invention, there is a method of forming a polyurethane sealant on a surface using the aforesaid two-part reaction
10 system and the catalyzed reaction mixture thereof. The polyurethane systems of the present invention are especially useful in sealing glass surfaces, such as glass windshields.

As used herein, these terms have the following meanings:

“Polyurethane” means a synthetic polymer formed by reacting hydroxyl
15 and isocyanate groups to give the urethane linkage group -NHC(O)O-;

“Gelation” means the point of cure where the mixture of sealant components achieves at least a five-fold increase in viscosity (in centapoise) in open air as compared to the initial viscosity of the mixture;

“Gel-time” or “Pot-life” have the same meaning for purposes of this
20 invention, and mean the duration of time required for the sealant to achieve gelation as determined from the time of admixture of the sealant components, i.e., the polyurethane-forming components;

“Isocyanate index” and “NCO-index” refer to the ratio of NCO groups over reactive hydrogen atoms present in a polyurethane formulation given as a
25 percentage:

$$\text{NCO-index} = \frac{(\text{NCO})}{(\text{active hydrogen})} \times 100;$$

“Active hydrogens” refers to the total of hydroxyl hydrogen atoms present in the reactive compositions, such as determinable by the Zerewitnoff test;

30 “Polyol” means a substance containing a stoichiometric average of at least 1.5 hydroxyl group attached per molecule;

"Polyurethane catalyst" means a substance capable of promoting the hydroxyl/isocyanate reaction forming the polyurethane;

"Bi/Zn Polyurethane catalyst" means a polyurethane catalyst comprised of a physical mixture of a catalytically-active bismuth compound and a zinc compound;

5 "Complexing agent" means a substance which forms a complex with the polyurethane catalyst which, at least temporarily, blocks or otherwise renders unreactive the catalyst;

"Mercaptan compound" means an organic compound having at least one -SH (mercapto) group;

10 "Molar excess", as used in connection with the complexing agent, means that the number of moles of mercaptan compound present exceeds the number of moles of catalyst present;

"Polyisocyanate" means a compound containing at least two -N=C=O groups;

15 "Toolable" means the capability of an applied bead of adhesive or sealant to be shaped out of its original form with pressure force exerted by a trowel or like device without substantial removal, transfer or loss of adhesive material from the bead;

"Reactive", as used to characterize the polyurethane-forming component system, means a material containing at least two different co-reactive monomers, oligomers or prepolymers capable of being polymerized after application to a substrate to form a three-dimensional polymeric network;

"Curable" has the same meaning as "reactive";

20 "Wetting" means the process in which a liquid spontaneously adheres to and spreads on a solid surface;

"Open time" or "induction time" means the time after the polyurethane-forming components are intimately mixed together to the gel time.

Other embodiments, features and advantages of the present invention will become apparent from the following drawings and description of the preferred
30 embodiments.

Figure 1 shows cure profiles for polyol/isocyanate systems using different catalytic systems involving Bi, Bi/Zn and Zn polyurethane catalysts each in combination with a mercaptan complexing agent.

5 Figure 2 shows cure profiles for polyol/poly- isocyanate systems using different types of mercaptan complexing agents.

Figure 3 shows cure profiles for polyol/poly- isocyanate systems in different types and levels of solvent.

10 The present invention, in its broadest concept, provides a catalyzed reaction mixture for producing a polyurethane, which catalyzed reaction mixture comprises a particular polyol component, a polyisocyanate component, and a particular complexed polyurethane catalyst.

15 Preferably, sealants of this type are stored prior to use in such a fashion that the catalyst and the isocyanate are not in contact with one another or are introduced to the enclosure immediately upon formulation. Various approaches are known for such separation, e.g., using a two-part caulking-like gun which has the isocyanate component in one reservoir, and the polyol component, catalyst and mercaptan compound in a second reservoir. For example, a two part plunger can be installed in the barrel portion of the caulk-like gun so that simultaneous ejection and mixture of the polyol and isocyanate compositions can be accomplished.

20 In a separate arrangement for storing and delivering the polyurethane-forming components of the invention, the polyol (and catalyst and mercaptan compound) and polyisocyanate components can be conveniently packaged in separate dual compartments of a moisture-proof hermetically-sealed flexible plastic package. The separate compartments of the package are sealed, such as by heat sealing, after
25 filling with the polyurethane-forming components, in a manner excluding all air from the compartment such that the volume of each compartment, as sealed, is the same as that of the polyurethane-forming materials filled therein. The dual compartments can be side-by-side and separated by a sealed membrane or wall of the flexible plastic located therebetween. For purposes of temporarily storing the polyurethane-forming
30 materials up until the mixing step, a part of the reaction system is placed in one open side compartment of the two-part bag. By way of explanation, in one embodiment, the two-part bag can be formed of a three-ply laminate sheet material of polyester and polyethylene

materials obtained under the tradename Scotchpak™ X29905 film commercially available from 3M, St. Paul, MN. This bag can be preformed of two superposed sheets of the Scotchpak™ film, the film being a three-ply laminate comprising a 0.5 mil (12.7 μm) medium density polyethylene film as an outer layer; a 0.5 mil (12.7 μm) polyester film as a middle layer; and a 3.5 mil (89 μm) low density polyethylene film as the innermost layer. The two sheets are heat sealed along a medial strip including a nonwoven strip material disposed in-between the two sheets at the site to be heat-sealed to form a ruptureable seal in-between the two compartments ultimately formed. A technique for forming a suitable two-part bag for this invention with a ruptureable seal therein is described in U.S. Patent No. 3,074,544 to Bollmeier. In this regard, the bag also is continuously heat sealed along its perimeter to seal the lateral side edges to form a compartment or pocket on each side of the medial ruptureable seal, except leaving one side of the formed compartment on each side of the ruptureable seal temporarily open until filled with a part of the reactant system. In order to bond the two superposed layers together to form the various seals, heat sealing methods and equipment used for sealing plastic bag materials that are common in the art can be suitably used. In any event, after filling a compartment with one part of the reaction system of the invention, the filled compartment is heat sealed at the last unsealed side edge of the sheets for that compartment, such as by an automatically controlled air operated heating bar sealer obtained from Pack-Rite Machines, Franksville, WI., to exclude all air from the filled pocket, thus forming a sealed pocket volume equal to that of the amount of formulation added thereto. Then, the second part of the reaction system of the invention is placed in the other side compartment of the bag located on the opposite side of the ruptureable seal, where the second compartment is formed in the same manner as first compartment, and then heat sealed to enclose the second part.

To provide even greater resistance against water vapor and moisture, or light, infiltration through the thickness of the bag, it is preferred to employ bleached kraft paper or aluminum foils as interior layers of the laminate film forming the walls of the bag. For example, the flexible package can be provided as a plastic/thin metal foil/plastic laminate with the metal foil representing the middle layer to prevent the contents of the package from being exposed to water and/or light before usage. In this embodiment, bag again is preformed of two superposed sheets of film, the film in this case being a three-ply laminate comprised of a 1 mil (25.4 μm) polyester film as an outer layer; a 0.35 mil (8.9

μm) aluminum foil film (1145 type) as a middle layer; and a 3.0 mil (76.2 μm) low density polyethylene film as the innermost layer. In another embodiment of the bag, bag again is preformed of two superposed sheets of film, the film in this case being a four-ply laminate comprised of a 25 lb. MG bleached kraft paper as an outermost layer; a 1 mil (25.4 μm)
5 polyester film immediately adjacent and beneath the kraft paper outermost layer; a 0.5 mil (12.7 μm) aluminum foil film (1145 type) as the next layer; and a 0.3 mil (7.6 μm) low density polyethylene film as the innermost layer of the film used to construct the bag.

When applying the sealer to a substrate, the general procedure is that contents of the bag compartments can be released from the compartments by rupturing
10 the middle seal to allow the contents of each side of the bag to intermingle; the bag is cut open at one end and the bag inserted into a chamber of a delivery device with the opened end oriented towards the outlet of the delivery device, such as a caulking gun; and the mixture discharged as a mixed coating stream onto a substrate. A retractible plunger mechanism can be used to force the mixed coating out of a nozzle part of the
15 device located at the opposite end of the delivery device. Known types of barrel and plunger sealant and caulk delivery devices in the field generally can be used in this regard.

Polyol Component

20 The polyol component may comprise one polyol or a combination of different polyols. As suitable polyols may be mentioned any of those utilizable for the production of polyurethanes. Such polyols are, in general, well known to those skilled in the art.

Polyols useful in the invention typically are liquid or quasi-liquid
25 polyols, with average functionality of from 1.5 or more, preferably a functionality of from 2 to 8, di-or trifunctional polyols being most preferred. Suitable polyols have a weight average molecular weight of about 400 to about 50,000, preferably from about 800 to 20,000.

Suitable polyols include a wide variety of polyether, polyester,
30 polyacrylic, polyvinyl, poly(epoxyester), polycarbonate, polyurethane and polyurea based polyols. These and other suitable polyols are well-known to those skilled in the art.

More specifically, suitable polyols may be selected from polyether polyols based on ethylene oxide, propylene oxide, butylene oxide, tetrahydrofuran, epichlorohydrin or mixtures thereof, ricinoleic acid derivatives, e.g., castor oil; polyester polyols, polyamide or polyesteramide polyols; tertiary amine containing polyols, e.g., ethoxylated or propoxylated amides or amines; polyalkadiene polyols derived from butadiene polymers or copolymers, and hydrogenated derivatives thereof; polyacetals, polycarbonates containing hydroxyl groups; polyhydroxyl (meth)acrylic resins, polythioether polyols, polymer polyols, and the like.

Also, suitable polyols are exemplified by EP 0454219, incorporated herein by reference, including certain polyester polyols and polyacrylic polyols. These suitable polyester polyols can be obtained, for instance, by the polycondensation of one or more di- and/or higher functional carboxylic acids with one or more di- and/or higher functional hydroxy compounds, optionally in combination with one or more monofunctional carboxylic acids and/or hydroxy compounds. The suitable acrylic polyols can be obtained, for instance, by the (co)polymerization of hydroxy-functional acrylic monomers with other ethylenically unsaturated comonomers in the presence of a free radical initiator.

The particular choice of polyol component, of course, depends upon a number factors including, primarily, the other components of the reaction mixture and the desired end use. These and other factors are well-known to those skilled in the art, who can make the proper selection of the polyol component accordingly.

Polyisocyanate Component

The polyisocyanate component may comprise one polyisocyanate or a combination of different polyisocyanates. As with the polyol component, as suitable polyisocyanates may be mentioned any of those utilizable for the production of polyurethanes. Such polyisocyanates are, in general, well known to those skilled in the art, and, for example, they are exemplified in U.S. 4,788,083 at column 8, line 63 through column 9, line 30.

The term isocyanate also includes isocyanate-terminated prepolymers. Polyisocyanates may be linear or branched, aliphatic, cycloaliphatic, arylalkyl, heterocyclic or aromatic, or any combination of such polyisocyanates. When the

isocyanate component contains only one compound, it preferably is an aliphatic isocyanate. Particularly suitable polyisocyanates correspond to the formula $Q(NCO)_n$ in which n is an integer of from about 2 to about 4, and Q is selected from an aliphatic hydrocarbon radical containing from about 2 to about 100 carbon atoms, and zero to 50 heteroatoms; a cycloaliphatic hydrocarbon radical containing from 4 to 100 carbon atoms and zero to 50 heteroatoms; an aromatic hydrocarbon radical or heterocyclic aromatic radical containing from 6 to 15 carbon atoms and zero to 10 heteroatoms, and an arylalkyl hydrocarbon radical containing from 8 to 100 carbon atoms and zero to 50 heteroatoms. The heteroatoms that can be present in Q include non-peroxidic oxygen, sulfur, non-amino nitrogen, halogen, silicon, and non-phosphino phosphorus.

Polyisocyanates preferably will have from about 2-4 isocyanate groups per molecule for use in the sealing/adhesive/coating composition of the present invention. Suitable polyisocyanates for use in the present invention include, for example, hexamethylene diisocyanate, 4,4'-toluene diisocyanate (TDI), diphenylmethane diisocyanate (MDI), polymethyl polyphenyl isocyanate (Polymeric MDI or PAPI), m- and p-phenylene diisocyanates, bitolylene diisocyanate, triphenylmethane triisocyanate, tris-(4-isocyanatophenyl)thiophosphate, cyclohexane diisocyanate (CHDI), bis-(isocyanatomethyl) cyclohexane (H_6XDI), dicyclohexylmethane diisocyanate ($H_{12}MDI$), trimethylhexane diisocyanate, dimer acid diisocyanate (DDI), dicyclohexylmethane diisocyanate, and dimethyl derivatives thereof, trimethyl hexamethylene diisocyanate, lysine diisocyanate and its methyl ester, isophorone diisocyanate, methyl cyclohexane diisocyanate, 1,5-naphthalene diisocyanate, triphenyl methane triisocyanate, xylylene diisocyanate and methyl and hydrogenated derivatives thereof, polymethylene polyphenyl isocyanates, chlorophenylene-2,4-diisocyanate, and the like and mixtures thereof. Aromatic and aliphatic polyisocyanate dimers, trimers, oligomers, polymers (including biuret and isocyanurate derivatives), and isocyanate functional prepolymers often are available as preformed packages and such packages are suitable for use in the present invention also.

The ratio of isocyanate equivalents of the polyisocyanate cross-linking agents to the hydroxyl groups from the hydroxy resinous materials preferably should be greater than about 1:1 and can range from about 1.05:1 up to about 1.5:1. At least a

slight excess of isocyanate is required in this invention to react with surface water (including water vapor) or water present in the polyol side of the system. The precise intended application of the sealing or coating composition often will dictate this ratio or isocyanate index. Therefore, the isocyanate index should be at least 100 or higher in value, preferably at least 105 to better ensure maintenance of adequate tensile and elongation properties. However, if the isocyanate index approaches about 150 or higher, the composition may be too rigid when cured to conform to the contours required.

10 Complexed Polyurethane Catalyst

The isocyanate groups of the polyisocyanate component react with the hydroxyl groups of the polyol component under the influence of the polyurethane catalyst to form urethane linkages. Suitable polyurethane catalysts for use with the present invention are complexed catalysts comprising a certain polyurethane metal catalyst complexed with a mercaptan compound.

15 Polyurethane Metal Catalyst

In general, these complexed polyurethane catalysts may be described as zinc and bismuth polyurethane catalysts which have been complexed (blocked) by reaction with a molar excess of a complexing agent selected from mercaptan compounds.

A wide variety of zinc and bismuth polyurethane catalysts are suitable for the combination, such bismuth neodecanoate and zinc neodecanoate. Such a catalyst is available as BICAT™ 8 from Shephard Chemical, which comprises a physical mixture of bismuth neodecanoate and zinc neodecanoate made with approximately equal amounts by weight based on the weight amounts of the Bi and Zn.

Suitable zinc and bismuth catalysts include salts of zinc and bismuth individually as any of organometallic chelates, alcoholates, phenolates, and salts of organic acids, tertiary amines, organic tin compounds, bicyclic amidines, aminosilanes, acidic metal salts of strong acids, tertiary phosphines, alkali and alkali earth metal hydroxides, and the like, and combinations thereof.

The amount of polyurethane catalyst (uncomplexed) generally ranges from about 0.01 to about 0.5 wt %, based upon the combined weight (solids) of polyol component and polyisocyanate component. This amount, of course, can vary widely depending, for example, on the particular components, desired end use, curing
5 conditions and other factors well-known and appreciable to those skilled in the art.

Complexing Agent

The complexing agent is used in conjunction with the bismuth and zinc catalyst. The complexing agent, for purposes of this invention, is a mercaptan
10 compound. It is not precisely known what dynamics occur to make the bismuth/zinc/mercaptan catalytic mixture produce a latent catalyst for catalyzing the chemical reaction between an isocyanate compound and a isocyanate-reactive compound, polyols, to form a product containing at least one urethane linkage. Without desiring to be bound by any particular theory at this time, it nonetheless is
15 thought that the mercaptan compound displaces some or all of the ligands on the bismuth/zinc catalysts which inhibits the metal catalysts' ability to catalyze the hydroxyl/ isocyanate reaction. The isocyanate functionality is reactive with the catalyst system used in this invention.

The mercaptan ligand reacts with the free isocyanate groups, forming
20 thiocarbamic linkages. It is believed that once the mercapto groups have been consumed, the hydroxyl/isocyanate reaction then becomes the predominate reaction. These theorized dynamics would account for the induction period or delay in the cure of the polyurethane.

It has been observed by present inventor that a wide variety of
25 mercaptans are useful to give an induction time. However, it is not precisely understood at this time why certain mercaptans are more efficient at giving a delay than others. By this, if each mercaptan is added to the polyurethane reaction mixture at a same level based on equivalents, it has been observed by the present investigator that the induction period varies from one compound to another. Under one possible theory,
30 if it is assumed that the mercaptan is binding to the metal atoms in the catalyst to produce the induction period, then it appears that bond energy is the key to induction. This behavior could be explained by steric effects. Consistent with this theory, it has

been observed by the inventor that mercaptopropyltrimethoxy silane gives an induction period which can vary from 5 to 20 minutes from sample to sample between polyurethane-forming systems of the same formulation. This difference, it is theorized, may be attributable by the ability of this compound to cyclize. The native noncyclic
5 form of the compound gives the delay, while the cyclic form would not have the mercapto group available to complex/bond to the metal atom of the catalyst.

A preferred mercaptan are those that are polyfunctional. By this, it is meant that the mercaptan compound has another group(s) in addition to the mercapto group(s) present which also can react with isocyanate. Examples of polyfunctional
10 mercaptans useful in the present invention include mercaptoethanol, $\text{HSCH}_2\text{CH}_2\text{OH}$, thioglycerol, and $\text{HSCH}_2\text{-CH(OH)CH}_2\text{OH}$.

On the other hand, the present inventor has also observed that polyfunctional mercaptan compounds had a tendency to precipitate from the reaction mixture and this may explain their diminished catalytic activity.

15 In a another embodiment, the mercaptan compound is selected from the group consisting of a mercaptoalkyl-alkoxy silane, a thioglycol, and an alkylthiol. Mercaptoalkoxy silanes provide adhesion promotion, especially to glass surfaces, which is contributed by these materials in addition to their complexing effect on the catalyst. On the other hand, as indicated above, the mercaptoalkoxy silanes, although
20 effective for meeting the requirement of the invention relating to providing a gel time between 5 and 60 minutes, have been observed in some cases to impart a less consistent and predictable extent of delay between 5 and 60 minutes from sample to sample, all other things kept equal. In any event, the mercapto-alkylalkoxy silane can be selected from a gamma-mercaptopropyl-trimethoxysilane, a gamma-mercaptopropyltriethoxysilane, a gamma-mercaptopropyl-methyldimethoxy silane, a
25 mercaptoethyltrimethoxysilane, and a beta-mercaptoethyltriethoxysilane.

The complexed polyurethane catalysts of this invention are produced by reacting the polyurethane catalyst with a molar excess of the complexing agent. As long as this requirement is met, the complexing agent/catalyst ratio may otherwise vary
30 widely. It is preferred, however, that the molar ratio of complexing agent to metal group of the catalyst ranges from about 2:1 to about 1000:1, more preferably from about 10:1 to about 100:1, and especially from about 10:1 to about 50:1.

Although the reactions to prepare the polyurethane-forming compositions of the present invention are preferably conducted at or near ambient temperature, it should be obvious to one skilled in the art that the reaction rate may be accelerated, if desired, by the application of elevated temperatures; although no heat
5 activation is required for the polyurethane-forming compositions of the present invention.

It is also possible to add other adjuvants to the above-described polyurethane-forming reactants so long as the addition thereof does not result in a loss of the required gel time and curing speeds. For example, the polyurethane-forming
10 compositions of this invention additionally can optionally contain opacifying pigments and inert extenders such as, for example, titanium dioxide, zinc oxide, clays such as kaolinite clays, silica, talc, carbon or graphite (e.g. for conductive coatings), and the like. Additionally, the coating compositions can contain tinctorial pigments, corrosion-inhibiting pigments, and a variety of agents typically found in coating compositions.
15 Such additional additives include, for example, surfactants, flow or leveling agents, pigment dispersants, and the like.

Fillers or combinations of fillers may also be present, such as glass or polymeric microspheres, glass fibers, graphite fibers, fibrous materials emanating from an organic polymer, carbon black, mica, aluminum oxide hydrates, various silicates or
20 carbonates or clays, fumed silica and the like. The term "filler" is used herein to include all solid additives including particulate matter or fibrous matter, present in the composition. Illustrative of the above materials is a fumed silica available under the trade name Cab-O-Sil™ from Cabot, and "Wollastonite", a clay filler available from Nyco Chemicals, Inc.

Also, certain reactive adjuvants can be added to either side (part) of the two-part polyurethane-forming system of the invention, or concurrently with the mixture of the two parts of the system, as long as the addition thereof does not result in a loss of the required gel time and curing speeds. For example, chain extenders can
25 be added and used to increase and tailor the polyurethane chain size. Useful chain
30 extenders for the present invention include diols and diamines such as 4,4'-methylene bis(2-chloro-aniline)("MOCA"), butane diol, hexane diol, propylene glycol, bisphenol A, or polyalkylene oxide polyols with weight average molecular weights between 100

and 500. The chain extenders can also be triols such as glycerine, trimethylol propane, or propoxylated adducts of glycerine or trimethylol propane or amines like diethyltoluene diamine, ethylene diamine, substituted aromatic diamines, triisopropyl amine, 4,4'-methylene-bis-(2,6-diethylaniline), methylene bis(orthochloro-aniline),
5 N,N-bis(2-hydroxypropyl)-aniline, and combinations thereof. Preferred chain extenders include 1,4-butane diol and 4,4'-methylene-bis-(2,6-diethylaniline), and combinations thereof.

The following nonlimiting examples will further illustrate the invention. All parts, percentages, ratios, and the like, in the examples are by weight unless
10 indicated otherwise.

EXAMPLES

Test Methods: Cure Profile Determination

Cure profiles were determined using a Brookfield Programmable
15 Rheometer (Model DV-III). The viscosities were determined in centapoise (cps) using the T-F spindle at 2 rpm in conjunction with the helipath at a temperature of 25°C and a relative humidity of approximately 50%. Both the viscosity and the temperature were measured versus time.

The two parts of the polyurethane-forming reactants were released
20 from the two compartments of a storage bag, described in more detail hereinafter, by rupturing an intervening temporary seal barrier formed between the two compartments, opening the bag by snipping an end, and squeezing the contents out of the bag into a mixing bowl, and then the contents were blended for 40 seconds in such a way that no air was whipped into the sample mixture. Immediately thereafter, between 90-110 g of
25 the reaction mixture is placed into a Dixie® cup, which was a truncated conical shape with a diameter at the top (mouth) of approximately 5.5 cm, a height of approximately 6 cm, and a diameter at the bottom of approximately 3.8 cm. The T-F spindle and temperature probe were quickly inserted and the viscosity and temperature of the reation mixture were recorded as a function of time (inclusive of the above-mentioned
30 40 seconds of preblending). The viscosity was measured until the viscosity reached 10,000,000 cps. The temperature probe was removed after the exotherm has been reached.

Part A

Example 1

To a 12 liter reaction vessel fitted with a nitrogen purge were added 4918 g of a polyether triol with an average molecular weight of 6000 obtained under the trade name E2306 from ARCO Chemical Company, 2420 g of a polyether diol having an average molecular weight of 2000 obtained under the trade name PPG 2025 from ARCO Chemical Company, 200 g of a polyether diol having an average molecular of 1000 obtained under the tradename PPG 1025 from ARCO Chemical Company, 825 g of a partially hydrogenated terphenyl as plasticizer obtained under the trade name HB 40 from Monsanto Co., and then 3500 g of 4,4'-diphenyl methane diisocyanate obtained under the trade name Mondur M from Miles Inc. was added thereto, and the mixture was allowed to react at 80°C with agitation. After the exothermic reaction ended, in which the temperature was not allowed to exceed 110°C, a prepolymer resulted with an isocyanate content of 8.1%.

Example 2

To a 12 liter reaction vessel fitted with a nitrogen purge were added 4735 g of a polyether diol with an average molecular weight of 4000 obtained under the trade name E2204 from ARCO Chemical Company, 1157 g of a polyether diol having an average molecular of 1000 obtained under the trade name PPG 1025 from ARCO Chemical Company, 1000 g of a plasticizer obtained under the tradename HB 40 from Monsanto Co., and then 3109 g of 4,4'-diphenyl methane diisocyanate obtained under the trade name Mondur M from Miles was added thereto, and the mixture was allowed to react at 80°C with agitation. After the exothermic reaction ended, in which the temperature was not permitted to exceed 110°C, a prepolymer resulted with an isocyanate content of 8.47%.

Part B

Example 3

To a 4 liter reaction vessel fitted with nitrogen purge were added 673.3 g of a polyether triol with an average molecular weight of 6000 obtained under the trade name E2306 from ARCO Chemical Company, 673.3 g of a polyether diol having an average molecular weight of 2000 obtained under the trade name PPG 2025 from ARCO Chemical

Company, 332 g of a polyether diol having an average molecular of 1000 obtained under the trade name PPG 1025 from ARCO Chemical Company, 117.0 g of 1,4-butanediol, 40.3 g of 4,4'-methylene-bis-(2,6-diethylaniline) obtained under the trade name Lonzacure M-DEA from Lonza Co., 32.0 g of (3-mercaptopropyl)trimethoxysilane obtained under the trade name A-189 from OSi Specialties Inc., and 2.1 g of a 50:50 mixture, by weight, of bismuth and zinc neodecanoates obtained under the trade name Bicat™ 8 from Shepherd Chemical Company, were mixed for 1 hr at 50°C with agitation.

Example 4-6

10 In formulating the polyurethane-forming reactant for each of Examples 4-6, the following general procedure was followed. To a 4 liter reaction vessel fitted with nitrogen purge were added about 670 g of a polyether triol with an average molecular weight of 6000 obtained under the trade name E2306 from ARCO Chemical Company, about 670 g of a polyether diol having an average molecular weight of 2000 obtained under the trade name PPG 2025 from ARCO Chemical Company, about 331 g of a polyether diol having an average molecular of 1000 obtained under the tradename PPG 1025 from ARCO Chemical Company, about 117 g of 1,4-butanediol, about 40.3 g of 4,4'-methylene-bis-(2,6-diethylaniline) obtained under the trade name Lonzacure M-DEA from Lonza Co., about 32 g of (3-mercaptopropyl)trimethoxysilane obtained under the trade name A-189 from OSi Specialties Inc., and 1.2 g of the catalyst indicated in Table 1 were mixed for 1 hr at 50°C with agitation. Table 1 summarizes the reagents and amounts (in grams) used in formulating each of Examples 4-6. Further, in Table 1, the meaning of other abbreviations used therein are as follows: "1,4-BDO" means 1,4-butanediol; "Bicat 8" means 50:50 mixture, by weight, of bismuth and zinc neodecanoates obtained from Shepherd Chemical Company; "Bicat Z" means zinc neodecanoate obtained from Shepherd Chemical Company; "Coscat 83" means bismuth neodecanoate obtained from CasChem Inc.

Table 1

Reagents	Examples		
	4	5	6
E2306	670.1	670.0	670.2
PPG 2025	670.2	670.2	670.2
PPG 1025	331.0	331.0	331.0
1,4-BDO	117.0	117.1	117.0
M-DEA	40.3	40.2	40.3
A-189	32.1	31.9	32.1
Bicat Z	1.2	-----	-----
Bicat 8	-----	1.2	-----
Coscat 83	-----	-----	1.1

Study One

Studies were undertaken to determine the effect of (3-mercaptopropyl) trimethoxysilane as the mercaptan complexing agent on various different polyurethane catalysts using the cure profile. In this study, Example 1 as Part A and Examples 4-6, respectively, as Part B, which had the formulations described above, were mixed together in amounts described herein providing an isocyanate index of 105.

For purposes of temporarily storing these formulations up until the mixing step, 100 g of the Example 1 formulation was placed in one open side compartment of a two-part bag. By way of explanation, the two-part bag was formed of a three-ply laminate sheet material of polyester and polyethylene materials obtained under the tradename Scotchpak™ X29905 film commercially available from 3M, St. Paul, MN. This bag was preformed of two superposed sheets each of a three-ply laminate comprising a 0.5 mil (12.7 μm) medium density polyethylene film as an outer layer; a 0.5 mil (12.7 μm) polyester film as a middle layer; and a 3.5 mil (89 μm) low density polyethylene film as the innermost layer. The two sheets were heat sealed along a medial strip including a nonwoven strip material disposed in-between the two sheets at the site to be heat-sealed to form a ruptureable seal in-between the two compartments ultimately formed. The technique for forming the two part bag of this study with a ruptureable seal is described in U.S. Patent No. 3,074,544 to Bollmeier. The bag also was continuously heat sealed along its perimeter

to seal the lateral side edges except leaving an end of each compartment temporarily open until filled with a part of the reactant system.

After filling a compartment with the 100 g of Example 1 formulation, the filled compartment was heat sealed at its end by an automatically controlled air operated heating bar sealer obtained from Pack-Rite Machines, Franksville, WI., to exclude all air from the filled pocket, thus forming a sealed pocket volume equal to that of the amount of formulation added thereto.

Then, 76 g of the Example 4, 5 or 6 formulation was placed in the other side compartment of the bag located on the opposite side of the ruptureable seal and heat sealed in the same manner as first compartment. As an extra precaution against moisture infiltration, the filled bag was stored in a dessicator jar until opened. The cure profile for the packaged polyurethane-forming reactants was later determined using the above mentioned Test Methods procedure. Figure 1 graphically shows the results of this Study One.

In Figure 1, curve "A" represents the system using Bicat 8 as the catalyst; curve "B" represents results for the system using Coscat 83 as the catalyst; and curve "C" represents the system using Bicat Z as the catalyst.

The gelation points for the polyurethane systems summarized in Figure 1 are indicated as occurring at that portion of the curves, if any, characterized by a rapid rise in the mixture temperature as a function of the time parameter, viz. a rise of at least 25°C in the mixture and occurring within a time span less than 10 minutes or less.

Examples 7-17

Additional samples of the part B side of the polyurethane-forming formulation was prepared according to the following general procedure. To a 4 liter reaction vessel fitted with nitrogen purge were added 349.2 g of a polyether diol with an average molecular weight of 6000 obtained under the trade name ARCOL 24-32 from ARCO Chemical Company, 349.2 g of a polyether triol having an average molecular weight of 2000 was obtained under the trade name ARCOL 34-28 from ARCO Chemical Company, 172.5 g of a polyether diol having an average molecular weight of 1000 obtained under the trade name Poly G 55-112 from Olin Chemical Company, 60.2 g of 1,4-butanediol, 21.1 g of 4,4'-methylene-bis-(2,6-diethylaniline) obtained under the trade name Lonzacure M-DEA from Lonza Co., 4.0 g of mercaptan in Examples 7-16 but not

Example 17, and 1.6 g of catalyst, were mixed for 1 hr at 50°C with agitation. The catalyst used was obtained under the tradename Bicat™ 8 from Shepherd Chemical Company, which catalyst was a physical mixture of bismuth neodecanoate and zinc neodecanoate made with approximately equal amounts by weight based on the weight amounts of the Bi and Zn.

The specific formulations for Examples 7-17 are summarized in Table 2 indicating the reagents and amounts (in grams) used for each example. In this regard, and further to the definitions provided above, in Table 2, "1,4-BDO" means 1,4-butanediol; thioglycerol means 3-mercapto-1,2-propanediol, obtained from Aldrich Chemical; "2-MTT" means 2-mercaptotoluimidazole, obtained from Aldrich Chemical; "2,3-DM-1,3,4-T" means 2,3-dimercapto-1,3,4-thiadiazole, obtained from Aldrich Chemical; "PETMP" means pentaerythritol tetrakis(3-mercaptopropionate), obtained from Aldrich Chemical; "GDMP" means "glycol dimercapto-propionate", obtained from Aldrich Chemical; "2-MBT" means 2-mercaptobenzimidazole, obtained from Aldrich Chemical; "2-MBT" means 2-mercaptobenzothiazole, obtained from Aldrich Chemical.

Table 2

Examples												
Reagents	7	8	9	10	11	12	13	14	15	16	17	
Arcol 24-32	349.20	349.20	349.20	349.20	349.20	349.20	349.20	349.20	349.20	349.20	349.20	
Arcol 34-28	349.20	349.20	349.20	349.20	349.20	349.20	349.20	349.20	349.20	349.20	349.20	
Olin 55-112	172.50	172.50	172.50	172.50	172.50	172.50	172.50	172.50	172.50	172.50	172.50	
1,4-BDO	60.20	60.20	60.20	60.20	60.20	60.20	60.20	60.20	60.20	60.20	60.20	
M-DEA	21.10	21.10	21.10	21.10	21.10	21.10	21.10	21.10	21.10	21.10	21.10	
Thioglycerol	4.0	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	
Capture 3-800	-----	4.0	-----	-----	-----	-----	-----	-----	-----	-----	-----	
Dodecylthiol	-----	-----	4.0	-----	-----	-----	-----	-----	-----	-----	-----	
A-189	-----	-----	-----	4.0	-----	-----	-----	-----	-----	-----	-----	
2-MTI	-----	-----	-----	-----	4.0	-----	-----	-----	-----	-----	-----	
2,3-DM-1,3,4-T	-----	-----	-----	-----	-----	4.0	-----	-----	-----	-----	-----	
PETMP	-----	-----	-----	-----	-----	-----	4.0	-----	-----	-----	-----	
GDMP	-----	-----	-----	-----	-----	-----	-----	4.0	-----	-----	-----	
2-MBI	-----	-----	-----	-----	-----	-----	-----	-----	4.0	-----	-----	
2-MBT	-----	-----	-----	-----	-----	-----	-----	-----	-----	4.0	-----	
Bicat 8	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	1.6	

Study Two

Experiments were undertaken to determine how the different mercaptans used in Examples 7-17 as used in conjunction with the Bicat 8 catalyst effected the induction period. In this study, Example 2 as Part A and Examples 7-17 as Part B, respectively, were mixed together in such a way that the isocyanate index was 105. 100 g of the Example 2 formulation was placed in one side of a same type of bag as used in Study One, as described above, heat sealed in the same manner as described for Examples 4-6, and 76 g of one of the Example 7-17 formulations was placed in the other side of the bag and heat sealed. The cure profile was determined using the above mentioned procedure and Figure 2 graphically shows the results of this study. In Figure 2, curve "D" represents the results for Example 7; curve "E" represents Example 8; curve "F" represents Example 9; curve "G" represents Example 10; curve "H" represents Example 11; curve "I" represents Example 12; curve "J" represents Example 13; curve "K" represents Example 14; curve "L" represents Example 15; curve "M" represents Example 16; and curve "N" represents Example 17.

Examples 18-23

For purposes of a study of the effect of solvent addition on the induction period, Examples 18-23 were prepared according to the following general procedure.

To a 200 liter reaction vessel fitted with nitrogen purge was added 57.7 kg of a polyether triol with an average molecular weight of 2000 obtained under the trade name ARCOL 34-28 from ARCO Chemical Company), 57.8 kg of a polyether diol having an average molecular weight of 6000 obtained under the trade name ARCOL 24-32 from ARCO Chemical Company, 28.6 kg of a polyether diol having an average molecular of 1000 obtained under the trade name Poly G 55-112 from Olin Chemical Co., 10.2 kg of 1,4-butanediol, 8.26 kg of 4,4'-methylene-bis-(2,6-diethylaniline) obtained under the trade name of Lonzacure M-DEA from Lonza Co., 670.0 g of 3-mercapto-1,2-propanediol obtained from Aldrich Chemical, and 290 g of catalyst (Bicat 8 obtained from Shepherd Chemical Company, and described above, were mixed for 1 hr at 50°C with agitation. This master batch was then divided into separate batches of 900 g or 950 g for Examples 18-23, as indicated in Table 3. Then various solvents as indicated in Table 3 were added in the amounts (in grams) indicated in Table 3 and thoroughly

mixed with the formulations of Examples 19-23, but not Example 18. In Table 3, "NMP" means N-methylpyrrolidinone, obtained from Aldrich Chemical; "TOL" means toluene, obtained from Aldrich Chemical; "MECL" means methylene chloride, obtained from Aldrich Chemical; and "MINSP" means mineral spirits.

5

Table 3

Reagents	Examples					
	18	19	20	21	22	23
Amt. of Master Batch	900	950	900	900	900	900
NMP	----	50	100	----	----	----
TOL	----	----	----	100	----	----
MECL	----	----	----	----	100	----
MINSP	----	----	----	----	----	100

Study 3

Experiments were undertaken to determine how the addition of solvent to Examples 18-23 as Part B effects the induction period. In this study, Example 2 as Part A and Examples 18-23 as Part B, respectively, were mixed together in such a way that the isocyanate index was 105. 100 g of the Example 2 formulation was placed in one side of a same type of bag as described for Study One above, heat sealed as in Study One, and 76 g of one of the Example 18-23 formulations was placed in the other side of the bag and heat sealed. The cure profile was determined using the above mentioned Test Methods procedure. Figure 3 graphically shows the results of this study.

In Figure 3, curve "O" represents Example 18; curve "P" represents Example 19; curve "Q" represents Example 20; curve "R" represents Example 21; curve "S" represents Example 22; and curve "T" represents Example 23.

In Figure 3, the gelation point for the various polyurethane systems corresponds to that portion of the respective curves, if any, characterized by an overall five-fold increase in the viscosity of the mixture as compared to the initial viscosity of the mixture. In the preferred polyurethane systems of the present invention, in the period of time of 5 to 60 minutes after admixture of the reactants, the systems show at least a

five-fold increase in viscosity within a time span of less than 10 minutes indicating an advantageous controlled onset of cure and relatively rapid cure.

While the invention has been described by reference to various specific and preferred embodiments and techniques, it is understood that many variations and
5 modifications can be made thereto without departing from the spirit and scope of the invention.

What is claimed is:

1. A two-part reaction system for producing a polyurethane having an isocyanate index of at least 100 and having a gel time between 5 and 60 minutes after admixture of said two parts, comprising first and second parts located in separate first and second containers, respectively, effective to prevent contact between said first and second parts thereof,
 - (a) said first part comprising a polyisocyanate component;
 - (b) said second part comprising
 - (i) a polyol component;
 - (ii) a polyurethane catalyst comprising a bismuth/zinc polyurethane catalyst; and
 - (iii) a molar excess of a complexing agent for said polyurethane catalyst, wherein said complexing agent comprises a mercaptan compound.
2. The two-part reaction system of claim 1, wherein said mercaptan compound is selected from the group consisting of a mercaptoalkylalkoxy silane, a thioglycol, and an alkylthiol or the group consisting of mercaptoethanol, $\text{HSCH}_2\text{CH}_2\text{OH}$, thioglycerol, $\text{HSCH}_2\text{CH}(\text{OH})\text{CH}_2\text{OH}$, and 3-mercaptopropyltrimethoxysilane.
3. The two-part reaction system of claims 1 or 2, wherein a molar ratio of said mercaptan compound to total metal of said polyurethane catalyst ranges from 2:1 to 1,000:1.
4. The two-part reaction system of any prior claim, wherein said bismuth/zinc polyurethane catalyst comprises a mixture of a bismuth salt and a zinc salt.
5. The two-part reaction system of claim 4, wherein said bismuth salt comprises bismuth neodecanoate and said zinc salt comprises zinc neodecanoate.

6. The two-part reaction system of claim 5, wherein said bismuth neodecanoate and said zinc neodecanoate are combined in approximately equal amounts by weight, based on the amount of metal in each said salt.

5 7. The two-part reaction system of any prior claim, wherein said polyisocyanate component and said polyol component are present in amounts providing an isocyanate index of from 105 to 150.

8. A catalyzed reaction mixture for producing a polyurethane having an
10 isocyanate index of at least 100, comprising a mixture of the two parts of any prior claim.

9. A method of forming a polyurethane sealant and/or adhesive on a surface comprising the steps of:

15 (a) mixing said first and second parts respectively of any of claims 1 to 8 at a temperature between -5°C and 40°C to provide a catalyzed reaction mixture;

 (b) applying said catalyzed reaction mixture to a surface at an ambient temperature of between -5°C to 40°C before said mixture reaches a gel time, wherein said gel time occurs between 5 and 60 minutes after step (a);

20 (c) allowing said catalyzed reaction mixture to reach said gel time at an ambient temperature of -5°C to 40°C to form a crosslinked polyurethane having an isocyanate index of at least 100 and being attached to said surface.

10. The method of claim 9, wherein said catalyzed reaction mixture is used
25 for attaching and sealing a curved glass sheet to a holding means;

 wherein said curved glass sheet has opposing major surfaces defining a continuous external peripheral side portion therebetween;

 wherein said holding means is a rigid apertured holding means completely enclosing an opening;

30 wherein said holding means includes a continuous interior peripheral portion defining an aperture and including a recessed profile adapted to receiveably engage and hold said continuous external peripheral side portion of said curved glass sheet;

wherein said catalyzed reaction mixture is applied to one of said recessed portion of said continuous interior peripheral portion or said continuous external peripheral side portion of said curved glass sheet, at an ambient temperature of between -5°C to 40°C before said mixture reaches a gel time;

5 wherein said gel time occurs between 5 and 60 minutes;

 wherein said curved glass sheet is positioned such that said continuous external peripheral side portion of said curved glass sheet is receivably engaged in said recessed portion of said continuous interior peripheral portion of said holding means; and

 whereupon said catalyzed reaction mixture is allowed to reach said gel time at
10 an ambient temperature of -5°C to 40°C to form a crosslinked polyurethane having an isocyanate index of at least 100 and effective to attach and seal said curved glass sheet to said holding means.

1/2




FIG. 1




FIG. 2

2/2




FIG. 3

INTERNATIONAL SEARCH REPORT

Internal Application No.
PCT/US 95/16516

A. CLASSIFICATION OF SUBJECT MATTER

C 08 G 18/22, C 08 G 18/08, C 09 D 175/04

According to International Patent Classification (IPC) or to both national classification and IPC⁶

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

C 08 G, C 09 D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, A, 5 011 902 (FOUCHT) 30 April 1991 (30.04.91), claims; table 4; column 9, lines 1-19. --	1, 4-9
A	US, A, 4 788 083 (DAMMANN et al.) 29 November 1988 (29.11.88), claims; column 3, lines 27-35; column 5, line 31; column 9, lines 31-35 (cited in the application). --	1-5, 7-9
A	EP, A, 0 454 219 (AKZO N.V.) 30 October 1991 (30.10.91), claims	1, 3, 9

☒ Further documents are listed in the continuation of box C.

☐ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

23 April 1996

Date of mailing of the international search report

15.05.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

WEIGERSTORFER e.h.

INTERNATIONAL SEARCH REPORT

Internat

Application No

PCT/US 95/16518

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
	(cited in the application). -----	

ANHANG

zum internationalen Recherchen-
bericht über die internationale
Patentanmeldung Nr.

ANNEX

to the International Search
Report to the International Patent
Application No.

ANNEXE

au rapport de recherche inter-
national relatif à la demande de brevet
international n°

PCT/US 95/16516 SAE 124596

In diesem Anhang sind die Mitglieder
der Patentfamilien der im obenge-
nannten internationalen Recherchenbericht
angeführten Patentdokumente angegeben.
Diese Angaben dienen nur zur Unter-
richtung und erfolgen ohne Gewähr.

This Annex lists the patent family
members relating to the patent documents
cited in the above-mentioned inter-
national search report. The Office is
in no way liable for these particulars
which are given merely for the purpose
of information.

La présente annexe indique les
membres de la famille de brevets
relatifs aux documents de brevets cités
dans le rapport de recherche inter-
national visée ci-dessus. Les renseigne-
ments fournis sont donnés à titre indica-
tif et n'engagent pas la responsabilité
de l'Office.

Im Recherchenbericht angeführtes Patentdokument Patent document cited in search report Document de brevet cité dans le rapport de recherche		Datum der Veröffentlichung Publication date Date de publication	Mitglied(er) der Patentfamilie Patent family member(s) Membre(s) de la famille de brevets	Datum der Veröffentlichung Publication date Date de publication
US A	5011902	30-04-91	keine - none - rien	
US A	4788083	29-11-88	AT A 7339/87 AT B 598573 AU A1 68684/87 AU B2 578741 BE AD 1001374 BR A 8701086 CA A1 1303015 CH A 67327 CN A 8710344 CN B 1007206 DD A 3290686 DD A3 3293635 DE A1 3709631 DE C 3709631 DK A 1311/87 DK B 1311/87 ES A 1676199 FI A 1000410 FI A 8027144 FI B 8027144 FI C 8027144 FI D 8027144 FI E 8027144 FI F 8027144 FI G 8027144 FI H 8027144 FI I 8027144 FI J 8027144 FI K 8027144 FI L 8027144 FI M 8027144 FI N 8027144 FI O 8027144 FI P 8027144 FI Q 8027144 FI R 8027144 FI S 8027144 FI T 8027144 FI U 8027144 FI V 8027144 FI W 8027144 FI X 8027144 FI Y 8027144 FI Z 8027144 FI AA 8027144 FI AB 8027144 FI AC 8027144 FI AD 8027144 FI AE 8027144 FI AF 8027144 FI AG 8027144 FI AH 8027144 FI AI 8027144 FI AJ 8027144 FI AK 8027144 FI AL 8027144 FI AM 8027144 FI AN 8027144 FI AO 8027144 FI AP 8027144 FI AQ 8027144 FI AR 8027144 FI AS 8027144 FI AT 8027144 FI AU 8027144 FI AV 8027144 FI AW 8027144 FI AX 8027144 FI AY 8027144 FI AZ 8027144 FI BA 8027144 FI BB 8027144 FI BC 8027144 FI BD 8027144 FI BE 8027144 FI BF 8027144 FI BG 8027144 FI BH 8027144 FI BI 8027144 FI BJ 8027144 FI BK 8027144 FI BL 8027144 FI BM 8027144 FI BN 8027144 FI BO 8027144 FI BP 8027144 FI BQ 8027144 FI BR 8027144 FI BS 8027144 FI BT 8027144 FI BU 8027144 FI BV 8027144 FI BW 8027144 FI BX 8027144 FI BY 8027144 FI BZ 8027144 FI CA 8027144 FI CB 8027144 FI CC 8027144 FI CD 8027144 FI CE 8027144 FI CF 8027144 FI CG 8027144 FI CH 8027144 FI CI 8027144 FI CJ 8027144 FI CK 8027144 FI CL 8027144 FI CM 8027144 FI CN 8027144 FI CO 8027144 FI CP 8027144 FI CQ 8027144 FI CR 8027144 FI CS 8027144 FI CT 8027144 FI CU 8027144 FI CV 8027144 FI CW 8027144 FI CX 8027144 FI CY 8027144 FI CZ 8027144 FI DA 8027144 FI DB 8027144 FI DC 8027144 FI DD 8027144 FI DE 8027144 FI DF 8027144 FI DG 8027144 FI DH 8027144 FI DI 8027144 FI DJ 8027144 FI DK 8027144 FI DL 8027144 FI DM 8027144 FI DN 8027144 FI DO 8027144 FI DP 8027144 FI DQ 8027144 FI DR 8027144 FI DS 8027144 FI DT 8027144 FI DU 8027144 FI DV 8027144 FI DW 8027144 FI DX 8027144 FI DY 8027144 FI DZ 8027144 FI EA 8027144 FI EB 8027144 FI EC 8027144 FI ED 8027144 FI EE 8027144 FI EF 8027144 FI EG 8027144 FI EH 8027144 FI EI 8027144 FI EJ 8027144 FI EK 8027144 FI EL 8027144 FI EM 8027144 FI EN 8027144 FI EO 8027144 FI EP 8027144 FI EQ 8027144 FI ER 8027144 FI ES 8027144 FI ET 8027144 FI EU 8027144 FI EV 8027144 FI EW 8027144 FI EX 8027144 FI EY 8027144 FI EZ 8027144 FI FA 8027144 FI FB 8027144 FI FC 8027144 FI FD 8027144 FI FE 8027144 FI FG 8027144 FI FH 8027144 FI FI 8027144 FI FJ 8027144 FI FK 8027144 FI FL 8027144 FI FM 8027144 FI FN 8027144 FI FO 8027144 FI FP 8027144 FI FQ 8027144 FI FR 8027144 FI FS 8027144 FI FT 8027144 FI FU 8027144 FI FV 8027144 FI FW 8027144 FI FX 8027144 FI FY 8027144 FI FZ 8027144 FI GA 8027144 FI GB 8027144 FI GC 8027144 FI GD 8027144 FI GE 8027144 FI GF 8027144 FI GH 8027144 FI GI 8027144 FI GJ 8027144 FI GK 8027144 FI GL 8027144 FI GM 8027144 FI GN 8027144 FI GO 8027144 FI GP 8027144 FI GR 8027144 FI GS 8027144 FI GT 8027144 FI GU 8027144 FI GV 8027144 FI GW 8027144 FI GX 8027144 FI GY 8027144 FI GZ 8027144 FI HA 8027144 FI HB 8027144 FI HC 8027144 FI HD 8027144 FI HE 8027144 FI HF 8027144 FI HG 8027144 FI HH 8027144 FI HI 8027144 FI HJ 8027144 FI HK 8027144 FI HL 8027144 FI HM 8027144 FI HN 8027144 FI HO 8027144 FI HP 8027144 FI HQ 8027144 FI HR 8027144 FI HS 8027144 FI HT 8027144 FI HU 8027144 FI HV 8027144 FI HW 8027144 FI HX 8027144 FI HY 8027144 FI HZ 8027144 FI IA 8027144 FI IB 8027144 FI IC 8027144 FI ID 8027144 FI IE 8027144 FI IF 8027144 FI IG 8027144 FI IH 8027144 FI II 8027144 FI IJ 8027144 FI IK 8027144 FI IL 8027144 FI IM 8027144 FI IN 8027144 FI IO 8027144 FI IP 8027144 FI IQ 8027144 FI IR 8027144 FI IS 8027144 FI IT 8027144 FI IU 8027144 FI IV 8027144 FI IW 8027144 FI IX 8027144 FI IY 8027144 FI IZ 8027144 FI JA 8027144 FI JB 8027144 FI JC 8027144 FI JD 8027144 FI JE 8027144 FI JF 8027144 FI JG 8027144 FI JH 8027144 FI JI 8027144 FI JJ 8027144 FI JK 8027144 FI JL 8027144 FI JM 8027144 FI JN 8027144 FI JO 8027144 FI JP 8027144 FI JQ 8027144 FI JR 8027144 FI JS 8027144 FI JT 8027144 FI JU 8027144 FI JV 8027144 FI JW 8027144 FI JX 8027144 FI JY 8027144 FI JZ 8027144 FI KA 8027144 FI KB 8027144 FI KC 8027144 FI KD 8027144 FI KE 8027144 FI KF 8027144 FI KG 8027144 FI KH 8027144 FI KI 8027144 FI KJ 8027144 FI KK 8027144 FI KL 8027144 FI KM 8027144 FI KN 8027144 FI KO 8027144 FI KP 8027144 FI KQ 8027144 FI KR 8027144 FI KS 8027144 FI KT 8027144 FI KU 8027144 FI KV 8027144 FI KW 8027144 FI KX 8027144 FI KY 8027144 FI KZ 8027144 FI LA 8027144 FI LB 8027144 FI LC 8027144 FI LD 8027144 FI LE 8027144 FI LF 8027144 FI LG 8027144 FI LH 8027144 FI LI 8027144 FI LJ 8027144 FI LK 8027144 FI LL 8027144 FI LM 8027144 FI LN 8027144 FI LO 8027144 FI LP 8027144 FI LQ 8027144 FI LR 8027144 FI LS 8027144 FI LT 8027144 FI LU 8027144 FI LV 8027144 FI LW 8027144 FI LX 8027144 FI LY 8027144 FI LZ 8027144 FI MA 8027144 FI MB 8027144 FI MC 8027144 FI MD 8027144 FI ME 8027144 FI MF 8027144 FI MG 8027144 FI MH 8027144 FI MI 8027144 FI MJ 8027144 FI MK 8027144 FI ML 8027144 FI MN 8027144 FI MO 8027144 FI MP 8027144 FI MQ 8027144 FI MR 8027144 FI MS 8027144 FI MT 8027144 FI MU 8027144 FI MV 8027144 FI MW 8027144 FI MX 8027144 FI MY 8027144 FI MZ 8027144 FI NA 8027144 FI NB 8027144 FI NC 8027144 FI ND 8027144 FI NE 8027144 FI NF 8027144 FI NG 8027144 FI NH 8027144 FI NI 8027144 FI NJ 8027144 FI NK 8027144 FI NL 8027144 FI NM 8027144 FI NO 8027144 FI NP 8027144 FI NQ 8027144 FI NR 8027144 FI NS 8027144 FI NT 8027144 FI NU 8027144 FI NV 8027144 FI NW 8027144 FI NX 8027144 FI NY 8027144 FI NZ 8027144 FI OA 8027144 FI OB 8027144 FI OC 8027144 FI OD 8027144 FI OE 8027144 FI OF 8027144 FI OG 8027144 FI OH 8027144 FI OI 8027144 FI OJ 8027144 FI OK 8027144 FI OL 8027144 FI OM 8027144 FI ON 8027144 FI OO 8027144 FI OP 8027144 FI OQ 8027144 FI OR 8027144 FI OS 8027144 FI OT 8027144 FI OU 8027144 FI OV 8027144 FI OW 8027144 FI OX 8027144 FI OY 8027144 FI OZ 8027144 FI PA 8027144 FI PB 8027144 FI PC 8027144 FI PD 8027144 FI PE 8027144 FI PF 8027144 FI PG 8027144 FI PH 8027144 FI PI 8027144 FI PJ 8027144 FI PK 8027144 FI PL 8027144 FI PM 8027144 FI PN 8027144 FI PO 8027144 FI PP 8027144 FI PQ 8027144 FI PR 8027144 FI PS 8027144 FI PT 8027144 FI PU 8027144 FI PV 8027144 FI PW 8027144 FI PX 8027144 FI PY 8027144 FI PZ 8027144 FI QA 8027144 FI QB 8027144 FI QC 8027144 FI QD 8027144 FI QE 8027144 FI QF 8027144 FI QG 8027144 FI QH 8027144 FI QI 8027144 FI QJ 8027144 FI QK 8027144 FI QL 8027144 FI QM 8027144 FI QN 8027144 FI QO 8027144 FI QP 8027144 FI QQ 8027144 FI QR 8027144 FI QS 8027144 FI QT 8027144 FI QU 8027144 FI QV 8027144 FI QW 8027144 FI QX 8027144 FI QY 8027144 FI QZ 8027144 FI RA 8027144 FI RB 8027144 FI RC 8027144 FI RD 8027144 FI RE 8027144 FI RF 8027144 FI RG 8027144 FI RH 8027144 FI RI 8027144 FI RJ 8027144 FI RK 8027144 FI RL 8027144 FI RM 8027144 FI RN 8027144 FI RO 8027144 FI RP 8027144 FI RQ 8027144 FI RR 8027144 FI RS 8027144 FI RT 8027144 FI RU 8027144 FI RV 8027144 FI RW 8027144 FI RX 8027144 FI RY 8027144 FI RZ 8027144 FI SA 8027144 FI SB 8027144 FI SC 8027144 FI SD 8027144 FI SE 8027144 FI SF 8027144 FI SG 8027144 FI SH 8027144 FI SI 8027144 FI SJ 8027144 FI SK 8027144 FI SL 8027144 FI SM 8027144 FI SN 8027144 FI SO 8027144 FI SP 8027144 FI SQ 8027144 FI SR 8027144 FI SS 8027144 FI ST 8027144 FI SU 8027144 FI SV 8027144 FI SW 8027144 FI SX 8027144 FI SY 8027144 FI SZ 8027144 FI TA 8027144 FI TB 8027144 FI TC 8027144 FI TD 8027144 FI TE 8027144 FI TF 8027144 FI TG 8027144 FI TH 8027144 FI TI 8027144 FI TJ 8027144 FI TK 8027144 FI TL 8027144 FI TM 8027144 FI TN 8027144 FI TO 8027144 FI TP 8027144 FI TQ 8027144 FI TR 8027144 FI TS 8027144 FI TT 8027144 FI TU 8027144 FI TV 8027144 FI TW 8027144 FI TX 8027144 FI TY 8027144 FI TZ 8027144 FI UA 8027144 FI UB 8027144 FI UC 8027144 FI UD 8027144 FI UE 8027144 FI UF 8027144 FI UG 8027144 FI UH 8027144 FI UI 8027144 FI UJ 8027144 FI UK 8027144 FI UL 8027144 FI UM 8027144 FI UN 8027144 FI UO 8027144 FI UP 8027144 FI UQ 8027144 FI UR 8027144 FI US 8027144 FI UT 8027144 FI UU 8027144 FI UV 8027144 FI UW 8027144 FI UX 8027144 FI UY 8027144 FI UZ 8027144 FI VA 8027144 FI VB 8027144 FI VC 8027144 FI VD 8027144 FI VE 8027144 FI VF 8027144 FI VG 8027144 FI VH 8027144 FI VI 8027144 FI VJ 8027144 FI VK 8027144 FI VL 8027144 FI VM 8027144 FI VN 8027144 FI VO 8027144 FI VP 8027144 FI VQ 8027144 FI VR 8027144 FI VS 8027144 FI VT 8027144 FI VU 8027144 FI VV 8027144 FI VW 8027144 FI VX 8027144 FI VY 8027144 FI VZ 8027144 FI WA 8027144 FI WB 8027144 FI WC 8027144 FI WD 8027144 FI WE 8027144 FI WF 8027144 FI WG 8027144 FI WH 8027144 FI WI 8027144 FI WJ 8027144 FI WK 8027144 FI WL 8027144 FI WM 8027144 FI WN 8027144 FI WO 8027144 FI WP 8027144 FI WQ 8027144 FI WR 8027144 FI WS 8027144 FI WT 8027144 FI WU 8027144 FI WV 8027144 FI WW 8027144 FI WX 8027144 FI WY 8027144 FI WZ 8027144 FI XA 8027144 FI XB 8027144 FI XC 8027144 FI XD 8027144 FI XE 8027144 FI XF 8027144 FI XG 8027144 FI XH 8027144 FI XI 8027144 FI XJ 8027144 FI XK 8027144 FI XL 8027144 FI XM 8027144 FI XN 8027144 FI XO 8027144 FI XP 8027144 FI XQ 8027144 FI XR 8027144 FI XS 8027144 FI XT 8027144 FI XU 8027144 FI XV 8027144 FI XW 8027144 FI XX 8027144 FI XY 8027144 FI XZ 8027144 FI YA 8027144 FI YB 8027144 FI YC 8027144 FI YD 8027144 FI YE 8027144 FI YF 8027144 FI YG 8027144 FI YH 8027144 FI YI 8027144 FI YJ 8027144 FI YK 8027144 FI YL 8027144 FI YM 8027144 FI YN 8027144 FI YO 8027144 FI YP 8027144 FI YQ 8027144 FI YR 8027144 FI YS 8027144 FI YT 8027144 FI YU 8027144 FI YV 8027144 FI YW 8027144 FI YX 8027144 FI YY 8027144 FI YZ 8027144 FI ZA 8027144 FI ZB 8027144 FI ZC 8027144 FI ZD 8027144 FI ZE 8027144 FI ZF 8027144 FI ZG 8027144 FI ZH 8027144 FI ZI 8027144 FI ZJ 8027144 FI ZK 8027144 FI ZL 8027144 FI ZM 8027144 FI ZN 8027144 FI ZO 8027144 FI ZP 8027144 FI ZQ 8027144 FI ZR 8027144 FI ZS 8027144 FI ZT 8027144 FI ZU 8027144 FI ZV 8027144 FI ZW 8027144 FI ZX 8027144 FI ZY 8027144 FI ZZ 8027144	
EP A1	454219	30-10-91	BR A 9101640 CA AA 2041060 JP A2 4227620	10-12-91 25-10-91 17-06-92